

Supplementary Materials

for

Effect of Polyelectrolyte Mono and Bilayer Formation on the Colloidal Stability of Layered Double Hydroxide Nanoparticles

Zoltán Somosi,^{1,2} Marko Pavlovic,¹ István Pálinkó³ and István Szilágyi^{1,2,*}

¹ MTA-SZTE Lendület Biocolloids Research Group, Department of Physical Chemistry and Materials Science, University of Szeged, H-6720 Szeged, Hungary

² Interdisciplinary Excellence Centre, Department of Physical Chemistry and Materials Science, University of Szeged, H-6720 Szeged, Hungary

³ Material and Solution Structure Research Group, Department of Organic Chemistry, University of Szeged, H-6720 Szeged, Hungary

* Correspondence: szistvan@chem.u-szeged.hu (I.S.)




Figure S1. Electrophoretic mobilities of LDH particles as a function of the PSS dose at 1 mM (circles), 10 mM (squares) and 100 mM (triangles) ionic strengths adjusted by NaCl. The measurements were carried out at 10 mg/L particle concentration. The mg/g unit on the x-axis indicates mg PSS per one gram of LDH. The lines serve to guide the eyes.




Figure S2. Electrophoretic mobilities of LDH-PSS particles as a function of the PDADMAC dose at 1 mM (squares), 10 mM (circles) and 100 mM (triangles) ionic strengths adjusted by NaCl. The measurements were carried out at 10 mg/L particle concentration. The mg/g unit on the x-axis indicates mg PDADMAC per one gram of LDH-PSS. The lines serve to guide the eyes.




Figure S3. Hydrodynamic radii of bare LDH (triangles), LDH-PSS (squares) and LDH-PSS-PDADMAC (circles) particles versus time at 3 mM ionic strength. Each data point is the average of 10 hydrodynamic radii measured in time-resolved DLS experiment. A PSS dose of 100 mg/g and PDADMAC of 300 mg/g was applied in the composite particles. The solid lines are linear fits, where the slope was set to zero.