



Layered double alkoxides a novel group of layered double hydroxides without water content

Gábor Varga, Márton Szabados, Ákos Kukovecz, Zoltán Kónya, Tamás Varga, Pál Sipos & István Pálinkó

To cite this article: Gábor Varga, Márton Szabados, Ákos Kukovecz, Zoltán Kónya, Tamás Varga, Pál Sipos & István Pálinkó (2020) Layered double alkoxides a novel group of layered double hydroxides without water content, Materials Research Letters, 8:2, 68-74, DOI: [10.1080/21663831.2019.1700199](https://doi.org/10.1080/21663831.2019.1700199)

To link to this article: <https://doi.org/10.1080/21663831.2019.1700199>



© 2019 The Author(s). Published by Informa UK Limited, trading as Taylor & Francis Group



Published online: 06 Dec 2019.



Submit your article to this journal [↗](#)



View related articles [↗](#)



View Crossmark data [↗](#)

ORIGINAL REPORT

OPEN ACCESS



Layered double alkoxides a novel group of layered double hydroxides without water content

Gábor Varga^{a,b}, Márton Szabados^{a,b}, Ákos Kukovecz^c, Zoltán Kónya^{c,d}, Tamás Varga^c, Pál Sipos^{b,e} and István Pálinkó^{a,b}

^aDepartment of Organic Chemistry, University of Szeged, Szeged, Hungary; ^bMaterials and Solution Structure Research Group and Interdisciplinary Excellence Centre, Institute of Chemistry, University of Szeged, Szeged, Hungary; ^cDepartment of Applied and Environmental Chemistry, University of Szeged, Szeged, Hungary; ^dMTA-SZTE Reaction Kinetics and Surface Chemistry Research Group, University of Szeged, Szeged, Hungary; ^eDepartment of Inorganic and Analytical Chemistry, University of Szeged, Szeged, Hungary

ABSTRACT


It has been generally accepted for long that water molecules are integral parts of layered double hydroxides (LDHs). It is even thought that in the absence of water molecules, there is no LDH structure. It is shown in this contribution that *via* the solvolysis of Mg- or Ca-alkoxides and Al-alkoxide with methanol or propanol and co-precipitated in methanolic methoxide, water-free LDH-like structures could be constructed. These novel LDH-like materials proved to be more active and selective catalysts in a Knoevenagel condensation than the corresponding 'classical' LDHs.

ARTICLE HISTORY

Received 5 September 2019

KEYWORDS

Water-free LDH; colloidal phase co-precipitation; alkoxide-solvolysis; solid base catalyst



IMPACT STATEMENT

Synthesis, thought to be not possible to prepare, characterization and a catalytic application of water-free LDHs are described. Water molecules are replaced by small alcohol molecules in the interlayer space.

Introduction

Clearly proven by the over ~ 30,000 articles published up to now since the nineties of the previous century that layered double hydroxides (LDHs), often called as anionic clays, became one of the most intensively studied material group.

Many scholars are working in this field, and this a broad one, spanning from intense research concerning the synthesis, modification and structural characterization of LDHs [1–6], through many applications like vehicles of medically important compounds [7–9] or polymer additives [10] to catalysis serving as catalysts either in their pristine layered forms [11–15] or after heat

treatment forming mixed oxides with many vacancies [16–23].

MgAl- and CaAl-LDHs, the most frequently used representatives of the group, have positively charged brucite- and portlandite-like layers, respectively, with interlayer regions containing fully or partially hydrated charge-compensating anions [24]. Water molecules not only serve as the hydrate shells of the interlayer anions, but they are situated at different positions of the interlayer space attaching to the layers with intermolecular hydrogen bonds of varying strengths [25].

Some examples can be found in the literature that the decrease in the water-content can bring important

CONTACT István Pálinkó palinko@chem.u-szeged-hu, palinko@chem.u-szeged.hu Department of Organic Chemistry, University of Szeged, Dóm tér 8, Szeged, H-6720 Hungary; Materials and Solution Structure Research Group and Interdisciplinary Excellence Centre, Institute of Chemistry, University of Szeged, Aradi Vértanúk tere 1, Szeged, H-6720 Hungary

Supplemental data for this article can be accessed here. <https://doi.org/10.1080/21663831.2019.1700199>

benefits. Alkoxide and transition metal-containing systems behave as 2D materials, which are easy to exfoliate and re-build as ultrathin films [26]. These films are excellent candidates for energy storage and conversion. Furthermore, water-free ZnAl films have photoluminescence property [27]. Moreover, having high surface area with notable porosity, the alcohol-treated systems were found to be better absorbent than pure LDH [28].

As it has been mentioned already, water molecules establish hydrogen-bonded networks in the interlayer space of the LDH. However, in principle, hydrogen-bonded networks may also be made by small alcohol molecules. These molecules may form the solvate shell of the charge-compensating anions as well. Thus, we set out to attempt the preparation of LDH-like structures, where water molecules are expected to be replaced by small alcohol molecules. For the attempted syntheses, the solvolysis of Mg(II) and Al(III) ethoxides or Ca(II) and Al(III) ethoxides were performed in a variety of alcohols at various temperatures, and they were co-precipitated in methanolic methoxide. Here, mainly results obtained with the Mg(II) ethoxide–Al(III) ethoxide system will be shown, for details of the results concerning the Ca(II) ethoxide–Al(III) ethoxide system, see the Supplementary Material (SM, all figures, the table and the scheme start with ‘S’) file.

Materials and methods

Synthesis of CaAl- and MgAl-layered alkoxides

All chemicals used were of analytical grade Sigma-Aldrich products, and were applied without further purification.

Water-free LDHs were prepared *via* the modified co-precipitation method: 0.015 mol of M(II) ethoxide and 0.0075 mol of M(III) ethoxide were solvolysed in 100 ml of methanol or ethanol or 2-propanol or propanol with constant stirring at 25 or 60°C for 24 h. The suspension obtained was dropped into a methanolic solution containing an appropriate amount of sodium methoxide to achieve the pH of precipitation. The 24 h room-temperature stirring of mixtures were followed by filtration, washing and drying (24 h, 25°C). All applied chemicals were water-free. The water contents of the solvents were removed using sodium-dosed distillation.

For comparison, nitrate-containing LDH samples were prepared by the co-precipitation method. As an example, for the synthesis of the pristine Ca₂Al–NO₃[–]–LDH/Mg₂Al–NO₃[–]–LDH samples, a mixture of Ca(NO₃)₂ × 4 H₂O/Mg(NO₃)₂ × 6 H₂O (30 mmol) and Al(NO₃)₃ × 9H₂O (15 mmol) was dissolved in 100 ml of distilled water and was stirred at pH 13 (set by 3 M

NaOH) for 12 h. The suspension was filtered and dried for 24 h at 60°C.

All operations were performed under N₂ atmosphere to avoid interlayer carbonate formation.

Characterization methods

Powder X-ray diffraction (XRD) patterns of the solid samples were recorded in the $2\theta = 5\text{--}60^\circ$ range (θ is the incidence angle of the X-ray beam) on a Philips PW1710 instrument with a secondary monochromator, using CuK α ($\lambda = 0.1542$ nm) radiation with 4°/min scanning step.

The morphology of the composites was studied by scanning electron microscopy (SEM). The SEM images were made on an S-4700 scanning electron microscope (SEM, Hitachi, Japan) with accelerating voltage of 10–18 kV. EDX data were obtained with a Röntec QX2 energy dispersive microanalytical system from two different parts of the sample. The coupled system also provided with the elemental map.

More detailed images could be recorded by transmission electron microscopy (TEM). A FEI TecnaiTM G2 20 X-Twin type instrument was used operating at an acceleration voltage of 200 kV.

A BIO-RAD Digilab Division FTS-65A/896 apparatus was available for IR spectroscopy measurements with 4 cm^{–1} resolution. The 4000–600 cm^{–1} ranges were recorded collecting 256 scans for each spectrum. Attenuated total reflection (ATR) mode was used for detection.

The ratio of metal ions was determined by Perkin Elmer Optima 7000DV Inductively Coupled Plasma Optical Emission (ICP-OES) spectrometer. Yttrium internal standard was used for each measurement. Before measurements, few milligrams of the samples measured by analytical accuracy were dissolved in 5 cm³ cc. HCl. After dissolution, the samples were diluted with distilled water to 100 cm³ and filtered.

Catalytic procedure for Knoevenagel condensation

Malononitrile (15.00 mmol), benzaldehyde (10.0 mmol) and dodecane as internal standard were mixed to get a clear solution using 3 cm³ ethanol as solvent. The reaction was quenched after 1–120 min with 6N HCl in ice-cold conditions. The product was extracted with ethyl acetate (3 × 10 cm³). The combined organic extracts were dried using anhydrous sodium sulphate, evaporated under reduced pressure, and assayed on a GC. Conversions in all cases were monitored with respect to the diminution of the aldehyde by gas chromatography. A Hewlett-Packard 5890 chromatograph equipped with

FID was employed for the analysis. The products were identified via using authentic samples.

Results and discussion

The effects of the solvents and the temperature of solvolysis for the material obtained from the solvolysis-co-precipitation of Mg(II) and Al(III) ethoxides are presented in Figure 1 through selected typical examples.

Application of water-free methanol, ethanol and 2-propanol did give diffractograms resembling those of the LDHs; however, the crystallinity of the structures obtained were rather poor in methanol at both temperatures, and side-products were observed in both ethanol and propanol even at 25°C. On applying propanol, XRD pattern resembling crystalline layered material was observed at both temperatures with somewhat sharper reflections at 60°C. These patterns were indexed on the basis of nitrate-containing Mg₂Al-LDH (JCPDS#70-2151). The ICP-OES analysis (supported by EDX measurements as well) resulted in 2.05:1 actual molar ratios for the Mg(II):Al(III) (it is 1.85:1 for Ca(II):Al(III) ratio) indicating similarity between the newly and the classically prepared (co-precipitation in basic aqueous ethanol) structure.

The SEM image of the material prepared at 60°C using propanol revealed hexagonal morphology like the LDHs (image A of Figure 2), and the TEM image further verified that a material was formed with hexagonally-shaped platelet-like particles (image B of Figure 2).

Similar observations were made for the Ca(II) ethoxide-Al ethoxide system solvolysed in propanol at 60°C (see, SFigures 1 and 2).

All these findings verify that layered materials were formed, indeed.

Further supporting characterization was performed by SEM-EDX measurements, for the EDX spectra and the elemental maps, see SFigures 3 and 4, and cell parameter data for the layered materials are given in STable 1.

The thermal decomposition profile (SFigure 5(a)) contains a sharp weight loss at 346°C not seen in the thermograms of LDHs prepared by aqueous precipitation (thermal decomposition profile of MgAl-CO₃²⁻-LDH is seen in SFigure 5(b) 3(b)). It is probably due to the decomposition of the interlayer alkoxide ions. The decomposition of the starting Mg(II)Al(III) ethoxide takes place under 300°C [29,30], i.e. the interlayer alkoxide ions are strongly fixed between the layers. The highest weight loss (30%) occurred at 120°C indicating the departure of interlayer propanol and methanol.

The TG/DTG thermograms for the Ca(II)Al(III) ethoxide can be found in the SM file as SFigures 6(a) and (b).

In the ATR-IR spectrum of the material prepared by solvolysis-co-precipitation from Mg(II) and Al(III) ethoxide (spectrum B of Figure 3) at 60°C, intense peaks are observed at around 1057 and 3645 cm⁻¹ associated with CO stretching vibration and isolated OH stretching vibration of primary alcohol. Another peak at around 1465 cm⁻¹ was attributed to bending vibration of




Figure 1. Selected XRD patterns obtained after the solvolysis-co-precipitation of Mg(II) and Al(III) ethoxides in (A) methanol at 25°C and (B) 60°C, (C) ethanol at 25°C, (D) 2-propanol at 25°C, (E) propanol at 25°C and (F) 60°C.




Figure 2. The (A) SEM and the (B) TEM images of the material prepared by solvolysis-co-precipitation of Mg- and Al-ethoxides at 60°C using propanol for solvolysis-co-precipitation.




Figure 3. IR spectra of (A) MgAl-NO₃⁻-LDH and (B) MgAl-LDA prepared by solvolysis-co-precipitation of Mg(II) and Al(III) ethoxides at 60°C.

CH (alkane) of alcohol [31]. Other characteristic peaks centred at about 2800–3000 cm⁻¹ were related to CH₃ stretching vibrations of alcohols [32,33]. Peaks at 1160 and 870 cm⁻¹ can be identified as CO stretching and CH₂ bending vibrations of longer chain alcohol (e.g. propanol), respectively [34].

Most importantly, the IR spectrum of the material does not contain the typical water H–O–H bending vibration around 1645 cm⁻¹, which is clearly detectable in the IR spectrum of the MgAl-NO₃⁻-LDH sample made by aqueous precipitation (spectrum A of

Figure 3). In addition, in the high wavenumber region, a new peak at about 3400–2600 cm⁻¹ was registered for the water-free sample composing of C–H stretching and the interlayer O–H stretching vibration modes typical of hydrogen-bonded systems [35] confirming that hydrogen-bonded alcohol molecules substituted the water molecules in this structure. The deconvoluted spectrum is displayed in Figure 4.

Similar assignation can be provided for CaAl-LDA.

These observations verify that indeed, a water-free layered substance is in our hands. This observation holds for




Figure 4. Deconvoluted IR spectrum of MgAl-LDA in the 3750–2550 cm^{-1} range.

the CaAl system as well (SFigure 7). From now on, these substances are going to be called water-free MgAl-LDA and water-free CaAl-LDA.

The storage time of LDA was 9 months in air. To our surprise, the degradation product could be isolated as Li methylcarbonate analogous structure by IR spectroscopy (SFigure 8). All the characteristic vibrations, such as the asymmetric (1590 cm^{-1}) and symmetric (1468 cm^{-1}) stretching vibrations of O–C–O in the monomer, the same vibration modes related to the dimer form (1405 , 1361 cm^{-1}) as well as the out-of-plane bending vibrations (873 , 830 cm^{-1}) proved the formation of metal methylcarbonate [36]. This observation indirectly supports that the synthesis of water-free LDA was successful, because this coordination compounds have already been produced by the interaction of inorganic methoxides (e.g. lithium methoxide) with CO_2 in (non-aqueous) methanol [37].

MgAl-LDHs prepared by the conventional aqueous co-precipitation method only displayed appreciable catalytic activities in the Knoevenagel condensation between benzaldehyde and malononitrile (SScheme 1) after heat-treatment [38] or doping with base [39] or in the presence of water [40]. Even after doping, the selectivity towards the condensation product was not 100%.

However, both water-free substances proved to be efficient, recyclable catalysts being fully selective towards the condensation reaction (Figure 5). For the optimization of




Figure 5. The yield of the Knoevenagel reaction over the various LDH-structured systems and the reusability of the materials. Conditions: benzaldehyde (10.0 mmol) and malononitrile (15.0 mmol); solvent-free, $m_{\text{cat}} = 0.2\text{ g}$, $T = 75^\circ\text{C}$.

catalyst loading, solvent used and reaction temperature, see, SFigure 9, STable 1, SFigure 10, respectively.

The addition product was fully transformed to the condensation product, which did not react any further, i.e. no Michael adduct could be observed. Hydrotalcites and hydrocalumites needed activation [37–41], while our water-free LDHs worked in their as-synthesized forms and under mild conditions (small amounts of catalysts, low reaction temperature, free of solvent and short reaction time).

Conclusions

On the basis of experimental results presented, it was shown that the generally accepted belief that LDHs must contain water molecules, can be circumvented. LDH-like structures could be prepared free of water by applying short-chain alcohols as the agents for solvolysis. XRD patterns and electron microscopy images and IR spectroscopy revealed ordered structures with hexagonally shaped morphologies, i.e. structures analogous to those of LDHs and water-free environments. The water free, as-prepared LDH-like substances proved to be active, highly selective and recyclable catalysts in the Knoevenagel condensation of benzaldehyde and malononitrile under mild reaction conditions unlike the analogous LDHs, which needed activation of some sort.

Acknowledgements

This work was supported by the Hungarian Government and the European Union through grant GINOP-2.3.2-15-2016-00013. The financial helps are highly appreciated. One of us, G. Varga thanks for the postdoctoral fellowship under the grant PD 128189.

Disclosure statement

No potential conflict of interest was reported by the authors.

Funding

This work was supported through the grant GINOP-2.3.2-15-2016-00013 and University of Szeged Open Access Fund.

References

- [1] Khan AI, O'Hare D. Intercalation chemistry of layered double hydroxides: recent developments and applications. *J Mater Chem.* **2002**;12:3191–3198.
- [2] Pavlovic M, Rouster P, Oncsik T, et al. Tuning colloidal stability of layered double hydroxides: from monovalent ions to polyelectrolytes. *ChemPlusChem.* **2017**;82:121–131.
- [3] Wu MJ, Wu JZ, Zhanggy J, et al. A review on fabricating heterostructures from layered double hydroxides for enhanced photocatalytic activities. *Catal Sci Technol.* **2018**;8:1207–1228.
- [4] Intasa-ard SG, Imwiset KJ, Bureekaew S, et al. Mechanochemical methods for the preparation of intercalation compounds, from intercalation to the formation of layered double hydroxides. *Dalton Trans.* **2018**;47:2896–2916.
- [5] Bukhtiyarova MV. A review on effect of synthesis conditions on the formation of layered double hydroxides. *J Solid State Chem.* **2019**;269:494–506.
- [6] Chatterjee A, Bharadiya P, Hansora D. Layered double hydroxide based bionanocomposites. *Appl Clay Sci.* **2019**;177:19–36.

- [7] Del Hoyo C. Layered double hydroxides and human health: an overview. *Appl Clay Sci.* **2007**;36:103–121.
- [8] Rives V, del Arco M, Martín C. Intercalation of drugs in layered double hydroxides and their controlled release: a review. *Appl Clay Sci.* **2014**;88–89:239–269.
- [9] Timóteo TRR, Melo CG, Danda LJA, et al. Layered double hydroxides of CaAl: a promising drug delivery system for increased dissolution rate and thermal stability of praziquantel. *Appl Clay Sci.* **2019**;180(105197):1–9.
- [10] Basu D, Das A, Stöckelhuber KW, et al. Advances in layered double hydroxide (LDH)-based elastomer composites. *Prog Polym Sci.* **2014**;39:594–626.
- [11] Fan G, Li F, Evans DG, et al. Catalytic applications of layered double hydroxides: recent advances and perspectives. *Chem Soc Rev.* **2014**;43:7040–7066.
- [12] Takehira K. Recent development of layered double hydroxide-derived catalysts – rehydration, reconstitution, and supporting, aiming at commercial application. *Appl Clay Sci.* **2017**;136:112–141.
- [13] Sipos P, Pálincó I. As-prepared and intercalated layered double hydroxides of the hydrocalumite type as efficient catalysts in various reactions. *Catal Today.* **2018**;306:32–41.
- [14] Ötvös SB, Pálincó I, Fülöp F. Catalytic use of layered materials for fine chemical syntheses. *Catal Sci Technol.* **2019**;9:47–60.
- [15] Qu J, Sha L, Wu C, et al. Applications of mechanochemically prepared layered double hydroxides as adsorbents and catalysts: a mini-review. *Nanomaterials.* **2019**;9(80):1–15.
- [16] Cavani F, Trifirò F, Vaccari A. Hydrotalcite-type anionic clays: preparation, properties and applications. *Catal Today.* **1991**;11:173–301.
- [17] Vaccari A. Preparation and catalytic properties of cationic and anionic clays. *Catal Today.* **1998**;41:53–71.
- [18] Monzon A, Romeo E, Marchi AJ. Layered double hydroxides. Rives V, editor. Huntington, NY: Nova Science Publishers, Inc; **2001**. p. 323–382.
- [19] Tichit D, Coq B. Catalysis by hydrotalcites and related materials. *Cattech.* **2003**;7:206–217.
- [20] Li F, Duan X. Applications of layered double hydroxides. *Struct Bond.* **2006**;119:193–223.
- [21] Xu ZP, Zhang J, Adebajo MO, et al. Catalytic applications of layered double hydroxides and derivatives. *Appl Clay Sci.* **2011**;53:139–150.
- [22] Li P, Yu F, Zhu M, et al. Two-dimensional layered double hydroxides for reactions of methanation and methane reforming in C1 chemistry. *Materials.* **2018**;11(221):1–27.
- [23] Wuttke S, Scholz G, Rudiger S, et al. Variation of sol-gel synthesis parameters and their consequence for the surface area and structure of magnesium fluoride. *J Mater Chem.* **2007**;17:4980–4988.
- [24] Mills SJ, Christy AG, Génin J-MR, et al. Nomenclature of the hydrotalcite supergroup: natural layered double hydroxides. *Miner Mag.* **2012**;76:1289–1336.
- [25] Bugris V, Haspel H, Kukovec Á, et al. Water types and their relaxation behavior in partially rehydrated CaFe-mixed binary oxide obtained from CaFe-layered double hydroxide in the 155–298 K temperature range. *Langmuir.* **2013**;29:13315–13321.
- [26] Carrasco JA, Romero J, Varela M, et al. Alkoxide-intercalated NiFe-layered double hydroxides magnetic

- nanosheets as efficient water oxidation electrocatalysts. *Inorg Chem Front.* **2016**;3:478–487.
- [27] Ruengkajorn K, Wright CM, Rees NH, et al. Aqueous immiscible layered double hydroxides – AIM-LDHs. *Mater Chem Front.* **2018**;2:2277–2285.
- [28] Prestopino G, Arrabito G, Generosi A, et al. Emerging switchable ultraviolet photoluminescence in dehydrated Zn/Al layered double hydroxide nanoplatelets. *Sci Rep.* **2019**;9:1–12.
- [29] Choudary BM, Kantam ML, Reddy CV, et al. Mg–Al–O–*t*-Bu hydrotalcite: a new and efficient heterogeneous catalyst for transesterification. *J Mol Catal A.* **2000**;159:411–416.
- [30] Siri-nguan N, Ngamcharussrivichai C. Alkoxide-intercalated Mg–Al layered double hydroxides as selective catalysts for the synthesis of monoglycerides. *Reac Kinet Mech Cat.* **2016**;119:273–289.
- [31] Kouzu M, Hidaka JS, Wakabayashi K, et al. Solid base catalysis of calcium glyceroxide for a reaction to convert vegetable oil into its methyl esters. *Appl Catal A.* **2010**;390:11–18.
- [32] Liu X, Piao X, Wang Y, et al. Calcium methoxide as a solid base catalyst for the transesterification of soybean oil to biodiesel with methanol. *Fuel.* **2008**;87:1076–1082.
- [33] Masood H, Yunus R, Choong TS, et al. Synthesis and characterization of calcium methoxide as heterogeneous catalyst for trimethylolpropane esters conversion reaction. *Appl Catal A.* **2012**;425–426:184–190.
- [34] Lynch CT, Mazdiyasi KS, Smith JS, et al. Infrared spectra of transition metal alkoxides. *Anal Chem.* **1964**;36:2332–2337.
- [35] Tainter CJ, Ni Y, Shi LA, et al. Hydrogen bonding and OH-stretch spectroscopy in water: Hexamer (cage), liquid surface, liquid, and ice. *J Phys Chem Lett.* **2013**;4:12–17.
- [36] Aurbach D, Daroux ML, Faguy PW, et al. Identification of surface films formed on lithium in propylene carbonate solutions. *J Electrochem Soc.* **1987**;134:1611–1620.
- [37] Zhuang GV, Xu K, Yang H, et al. Lithium ethylene dicarbonate identified as the primary product of chemical and electrochemical reduction of EC in 1.2 M LiPF₆/EC: EMC electrolyte. *J Phys Chem B.* **2005**;109:17567–17573.
- [38] Climent MJ, Corma A, Iborra S, et al. Increasing the basicity and catalytic activity of hydrotalcites by different synthesis procedures. *J Catal.* **2004**;225:316–326.
- [39] Devi R, Begum P, Bharali P, et al. Comparative study of potassium salt-loaded MgAl hydrotalcites for the Knoevenagel condensation reaction. *ACS Omega.* **2018**;3:7086–7095.
- [40] Ebitani K, Motokura K, Mori K, et al. Reconstructed hydrotalcite as a highly active heterogeneous base catalyst for carbon–carbon bond formations in the presence of water. *J Org Chem.* **2006**;71:5440–5447.
- [41] Shirotori M, Nishimura S, Ebitani K. Genesis of a bifunctional acid–base site on a Cr-supported layered double hydroxide catalyst surface for one-pot synthesis of furfurals from xylose with a solid acid catalyst. *Catal Sci Technol.* **2016**;6:8200–8211.